



AeroMarine Products, Inc.
8659 Production Avenue
San Diego, CA 92121
(877) 342-8860

www.aeromarineproducts.com
info@aeromarineproducts.com

How to use AeroMarine Polyurethane Pour-In-Place Foam

Physical Properties:

Parallel to Rise Compressive Strength: 40 psi

Tensile Strength: 30 psi

Shear Strength: 30 psi

Flexural Strength: 50 psi

Material

AeroMarine Pour-in-Place Foam is a two part, 2 LB per cubic foot density foam designed for use in filling cavities and voids for positive flotation. It is also an excellent insulator for use around fridges and freezers and can be sanded into any shape once cured. Pour-In-Place Foam can be covered with polyester resin mat and woven roving or epoxy resin with cloth, to give a strong and durable finish.

Mixing

Pour-In-Place Foam is mixed in a 1:1 ratio, mixing only small amounts at one time. Mixing time is approximately 20 - 30 seconds and working time is one minute. The foam will fill about one cubic foot per quart of mixed liquid at 72 F. If the foam is mixed at a lower temperature it will be much denser and more product will be needed to complete the job.

Application

AeroMarine Pour-In-Place Foam is designed for use in filling cavities and voids. It can not be free formed and therefore must be contained on all sides in order to completely fill the void. If a release off the surface is required, a poly sheet such as a garbage bag should be used due to the excellent adhesive quality of the foam.

Example

When filling a boat hull between stringers, mix a cup of each component in a clean container. Mix rapidly for 20 - 30 seconds and pour into the deepest part of the cavity. If the floor board is not glassed in place, wrap a poly garbage bag around it and place it on top of the stringers. The foam will expand upwards, hit the floor board and start to fill the remainder of the cavity. Simply repeat this procedure until the cavity is filled and glass the floor board in place.

Clean Up

The "A" part of the foam cleans up with acetone and the "B" part with water. Due to the adhesive quality of the foam, keep the mixed product off everything except the job itself.

Tips

- Heat foam in hot tap water if air temperature is lower than 65F.
- Only mix small quantities of Part "A" and Part "B" at one time.
- Heat the cavity the foam is to be poured into, if it is cold to the touch.



AeroMarine Products, Inc.
8659 Production Avenue
San Diego, CA 92121
(877) 342-8860

www.aeromarineproducts.com
info@aeromarineproducts.com

AeroMarine 2# Density Foam Features

- (1) Low viscosity
- (2) Convenient volumetric mix ratio
- (3) Rapid set time
- (4) No odor
- (5) Easily carved and machined
- (6) Excellent base for polyester/fiberglass
- (7) Readily accepts paints, stains and finishes
- (8) This foam has been tested in accordance with U.S. Coast Guard Regulation # 33 CFR 183.114

This system expands to a foam approximately 25 times the liquid volume. As a rule of thumb, a 2-gallon kit will fill about 8 cubic feet of space. If 2 lbs per cubic foot is not dense enough, we also stock higher density foam.

The resultant room temperature cured plastic foam has these properties:

Cured Density: 2 lbs/ cubic foot

Compressive strength: 40 psi

K-factor: 0.22

R- Value: 7 per inch

AeroMarine Products (seller) make no warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. User is responsible for determining whether the seller's product is fit for a particular purpose and suitable for a user's particular method of application. Many factors can affect the use and performance of seller's product. Given the variety of factors that can affect the use and performance of seller's product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the seller's product to determine whether it is fit for a particular purpose and is suitable for the user's method of application.

If the seller's product is proven to be defective, THE EXCLUSIVE REMEDY, AT SELLER'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE PRODUCT. Seller shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.