AeroMarine Products Silicone Thickener

AeroMarine Products Silicone Thickener can be added to any AeroMarine Products 10:1 tin based (condensation cure) silicone rubber RTV to create a thixotropic, brushable material. **Do not use with simple 1:1 silicones.** This special additive must be added at the time of mix, to the white silicone base (Part A) prior to adding the catalyst.

To use, add about 1% Thickener to the part A (white silicone base), then add the catalyst. Use more or less to make the final product the desired viscosity. Do not add more than 10%, as more than 10% will degrade the quality of the finished mold.

FOR INDUSTRIAL OR PROFESSIONAL USE ONLY